

TEST REPORT

No.: SHIN1808058863MR

Date: Aug 20, 2018

Page: 1 of 3

CUSTOMER NAME: WUXI KAIJIEDA PLASTIC PRODUCTS FACTORY

ADDRESS: HENGTONG ROAD, YANGSHAN SUPPORTING AREA, HUISHAN

ECONOMIC DEVELOPMENT ZONE, WUXI JIANGSU, CHINA

Sample Name : PVC DOOR JAMB

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

SGS Ref. No. : NJIN1808003740ML

Date of Receipt : Aug 14, 2018
Testing Start Date : Aug 14, 2018
Testing End Date : Aug 20, 2018

Test result(s) : For further details, please refer to the following page(s)

(Unless otherwise stated the results shown in this test report refer only to

the sample(s) tested)

Signed for SGS-CSTC Standards Technical Service (Shanghai)Co., Ltd.

Xia Hai

Authorized signatory





TEST REPORT

No.: SHIN1808058863MR

Date: Aug 20, 2018

Page: 2 of 3

Summary of Results:

No.	Test Item	Test Method	Result	Conclusion
1	Vicat Softening	ISO 306:2013 Method	63.8 °C	,
	Temperature	B50		/

Note: Pass: Meet the requirements;

Fail: Does not meet the requirements;

/: Not Apply to the judgment.





TEST REPORT

No.: SHIN1808058863MR

Date: Aug 20, 2018

Page: 3 of 3

Test Item: Vicat Softening Temperature Sample Description: White plastic part Test Method: ISO 306:2013 Method B50

Test Condition:

Specimen thickness: 5.27 mm Heat-transfer media: Silicone oil Rate of temperature: 50 K/h

Load: 50N


Lab Environmental Condition: 23 ± 2 °C, 50 ± 5 %RH

Test Result:

Test Item	Test Result
Vicat Softening Temperature	63.8 °C

Note: Test specimens were cut from the sample.

Original Sample Photo:



****** End of report******



No.69, Block 1159, East Kang Qiao Road, Pudong District, Shanghai, China 201319 中国・上海・浦东康桥东路1159弄69号

t (86-21) 61196300 t (86-21) 61196300 邮编: 201319

f(86-21) 68183122/68183920 www.sgsgroup.com.cn

f(86-21) 68183122/68183920 e sgs.china@sgs.com